

Product Specification Sheet

Calcium Lignosulphonate

No. SMRP023-0

| Other Names | Calcium Lignosulfonate | | |
|---------------------------------|---|---------------|------------------|
| Items/Grades | CL-65 | CL-60 | CL-50 |
| Appearance | Pale Brown Powder | Yellow Powder | Yellow Powder |
| Lignosulphonate Content (%) | ≥ 65 | ≥ 60 | ≥ 50 |
| Sugar Content (%) | 3-5 | 6-9 | 8-10 |
| Calcium Content (%) | 10-12 | 5-7 | 4-6 |
| Dry Matter (%) | ≥ 95 | ≥ 95 | ≥ 94 |
| Ash (%) | ≤ 13 | ≤ 13 | ≤ 14 |
| Water Insoluble (%) | ≤ 0.5 | ≤ 0.5 | ≤ 1 |
| Moisture (%) | ≤ 5 | ≤ 5 | ≤ 5 |
| PH Value (10% Aqueous Solution) | 6.5-7.8 | 4-7 | 4-6 |
| Fineness (0.18~0.125mm, %) | 95min | 95min | 95min |
| Packing | 25kg in one paper bag and 500-700 kg on one pallet, 10-14 metric tons/20'FCL. | | |
| Ligno Resource | Pine Pulp | Poplar Pulp | Wheat Straw Pulp |

Siamatec



Luoyang Siamatec Co., Ltd

1202, Guobao Building, 261 Kaiyuan Avenue, Luoyang 471026, China

Tel: +86-379-6333-8196/8 Fax: +86-379-6333-8197 Email: info@siamatec.com