


Expanded Clay Aggregate

No. SMRP016-0

Other Names		Expanded Tenacious Clay	
Items/Grades		EC-1.5	EC-1.6
Chemical Compositions (%)	Al ₂ O ₃ Fe ₂ O ₃	>=40 <=3	>=40 <=3
Bulk Density (g/cm ³)		<=1.5	<=1.6
Compressive Strength (Mpa)		>=6	>=7
Water Absorption (%)		<=20	<=15
Refractoriness (°C)		>=1,670	>=1,670
Loss on Ignition (%)		<=0.5	<=0.5
Particle Size	8-15mm, 5-8mm, 3-5mm, 5-3mm, etc.		
Packing	1,000 ~ 1,250kg in one jumbo bag, 20 ~ 25MT in 1x20'fcl		
Photos for Reference			

Siamatec



Siamatec

Luoyang Siamatec Co., Ltd

1202, Guobao Building, 261 Kaiyuan Avenue, Luoyang 471026, China

Tel: +86-379-6333-8196/8 Fax: +86-379-6333-8197 Email: info@siamatec.com