


Product Specification Sheet

Kyanite

No. SMRP013-0

Other Names		Cyanite, Disthene, Rhoetzite, Sappare			
Items/Grades		K-50	K-55	K-58	K-60
Chemical Compositions (%)	Al ₂ O ₃	50-55	55-58	58-60	60-63
	SiO ₂	45-50	40-45	37-42	35-40
	Fe ₂ O ₃	<=0.8	<=0.8	<=0.6	<=0.5
	TiO ₂	<=0.5	<=0.5	<=0.5	<=0.5
	K ₂ O+Na ₂ O	<=0.1	<=0.1	<=0.1	<=0.1
	CaO+MgO	<=0.5	<=0.5	<=0.5	<=0.5
Physical Properties	Moisture (%)	<=0.8	<=0.8	<=0.8	<=0.8
	Loss on Ignition (%)	<=0.5	<=0.5	<=0.5	<=0.5
	Refractoriness (°C)	>=1,790	>=1,790	>=1,790	>=1,790
	Linear Change (%) (1350 °Cx2hrs)	-2 ~ +6	-2 ~ +6	-2 ~ +6	-2 ~ +6
Particle Size		40-80mesh, 40-200mesh, 80-120mesh, 100-120mesh, 200-325mesh, etc.			
Packing		1,000 - 1,250kg in one jumbo bag, 20 - 25MT in 1x20'fcl			
Photos for Reference					

Siamatec



Luoyang Siamatec Co., Ltd

1202, Guobao Building, 261 Kaiyuan Avenue, Luoyang 471026, China

Tel: +86-379-6333-8196/8 Fax: +86-379-6333-8197 Email: info@siamatec.com